



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Hytrel

Suebel Code : HYT-1

Revision date : 01/03/2009

Physical properties	nominal	actual	units
Density ASTM D 792, 23 °C	1.20-1.24	1.22	g/cm ³
Hardness ASTM D 2240, 23 °C	63	63	Shore D
Hardness ASTM D 2240, 23 °C	97-99	98	Shore A
Tensile strength ASTM D 638, 23 °C	41	44	Mpa
Elongation at break ASTM D 638, 23 °C	420	440	%
Heat Distortion ISO 72 2, Temp at 0.5mpa	---	115	°C
Operating Temp Range	---	-50 to 110	°C

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB