



Groot-Bijgaardenstraat 124
B-1620 Drogenbos

Material : Nitrile Butadiene Rubber

Suebel Code : NT 4B

Revision date : 01/04/2015

Physical properties	nominal	actual	units
Hardness BS 903 A 26, 23 °C	70-75	72	Shore A-2
Tensile strength BS 903 A 2, 23 °C	> 102	160	Kg/Cm ²
Elongation at break BS 903 A 2, 23 °C	> 250	350	%
Compression set BS 903 A 6, 100 °C, 22 h, 25 %	< 25	21.5	%
Air Ageing BS 903 A 19, 100 °C, 70 h			
Hardness Change	<(+15)	+2	Points
Tensile Change	<(-20)	-9.3	%
Elongation Change	<(-40)	-14.2	%
Fluid Resistance, ASTM Oil-1 BS 903 A 16, 100 °C, 70 h			
Hardness Change	-5 to +15	+2	Points
Tensile Change	<(-25)	-10.8	%
Elongation Change	<(-45)	-21.5	%
Volume Change	-10 to +5	-4.2	%
Fluid Resistance, ASTM Oil-3 BS 903 A 16, 100 °C, 70 h			
Hardness Change	<(-15)	-3	Points
Tensile Change	<(-45)	-12.7	%
Elongation Change	<(-45)	-22.8	%
Volume Change	-0 to +35	+14	%
Specific Gravity BS 903 A 1, 23 °C	---	1.206	Gm/cc
Ash Content 800°C, 2 Hrs	---	7.45	%
Operating Temperature	-30°C To +100°C		

RC Bruxelles 543672
TVA : BE 443 660 083
Fortis Bank

Tel : 00 32 2 – 331 25 32
Fax : 00 32 2 – 378 15 16
IBAN : BB88 2100 9023 8041

Web : www.suebel.be
Email : sales@suebel.be
Swift (BIC) : GEBABEBB